

INATECH®

Packaging Supplies & Equipment

FISA TEHNICA

CARTON ROLA TESTLINER



INATECH PACKAGING

Strada Tudor Vladimirescu, Nr. 393

Domnești - Ilfov

Telefon / Fax: 021 448.03.58

Strada Calea Clujului, Nr. 271, Oradea

office@inatech.ro

www.inatech.ro

www.ifoam.ro

www.inatech-shop.ro

www.izolatie-reflectiva.ro

INATECH®

Packaging Supplies & Equipment

CARACTERISTICI TEHNICE

Carton rola testliner maro, realizat din fibre reciclabile 100% (Cod 30 CEPI)

DESCRIERE	GRAMAJ NOMINAL g/m ²	GRAD UMEZEALA %	REZISTENTA kPa	SCT-CD kN/m	Cobb 60 g/mp
Metoda De Testare	ISO 536	ISO 20287	ISO 2287	ISO 9895	ISO 20535
Toleranta	+/-3%	+/-1,5%	+/-10%	+/-10%	max
TESTLINER 110g/m ²	110	7,5%	250	1,55	40
TESTLINER 115g/m ²	115		260	1,65	
TESTLINER 120g/m ²	120		270	1,80	
TESTLINER 125g/m ²	125		280	1,85	
TESTLINER 130g/m ²	130		290	2,00	
TESTLINER 140g/m ²	140		310	2,20	
TESTLINER 150g/m ²	150		320	2,30	
TESTLINER 160g/m ²	160		330	2,40	
TESTLINER 170g/m ²	170		340	2,50	

